

# MasterKure<sup>®</sup> 106

(Formerly known as MasterKure 106)

Water based concrete curing compound

## DESCRIPTION

**MasterKure 106** is a solvent free, membrane forming wax emulsion, suitable for spray application to freshly poured concrete.

The resultant film retains sufficient moisture in the concrete to ensure full hydration of the cement; essential for optimum strength development. Membrane cured concrete is typically harder and exhibits a dust free surface with a reduced incidence of drying shrinkage cracks.

## PRIMARY USES

As a more effective and economical alternative to hessian and water and polythene curing regimes. Suitable for use on all concrete surfaces.

## ADVANTAGES

- Eliminates the need for water.
- Single application.
- Promotes a harder dust free surface.
- Cured film is clear and water repellent.
- Reduces drying shrinkage.
- High curing efficiency.
- Reduced labour costs.
- Water based.

## PACKAGING

**MasterKure 106** is available in 200 litre drums.

## TYPICAL PROPERTIES\*

Appearance:	White Milky liquid
Specific gravity:	1.00 – 1.02
Flashpoint:	Not applicable
Finished film appearance:	Clear, tack free, water repellent film
Water retention	Pass
ASTM C156:	
Drying time	3 hours 45 minutes
ASTM C309:	

## STANDARDS

ASTM C309 Type 1 Class A AASHTO M-148 Type 1 Class A

## DIRECTIONS FOR USE

The compound should be spray applied as evenly as possible on to the freshly placed concrete.

For horizontal surfaces **MasterKure 106** should be applied as soon as the initial surface sheen has disappeared from the concrete surface. In the case of formed concrete, the **MasterKure 106** should be applied immediately on removal of the formwork. To assist breakdown of the **MasterKure 106** film on vertical and formed surfaces, it is essential to dampen down the concrete with clean water prior to application.

## COVERAGE

The recommended rate of application is 5-6 square metres per litre. This corresponds to that at which **MasterKure 106** has been tested, and at which it attains the claimed degree of curing efficiency. In favourable conditions such as shaded interior surfaces, adequate curing can be achieved with extended coverage rates.

## FILM BREAKDOWN

The time for deterioration of the membrane is dependent on a number of variables, which include film thickness, degree of exposure to weathering, traffic UV light, and the porosity of the substrate concrete.

## SUBSEQUENT SURFACE FINISHES

It is important that the complete removal of the **MasterKure 106** should be ensured prior to the application of any surface finish or additional treatment. It is recommended that where the concrete is to receive



The Chemical Company

# MasterKure<sup>®</sup> 106

(Formerly known as MasterKure 106)

a coating or the application of tiles, the use of **MasterKure 181** is considered.

**MasterKure 181** is a resin based non degrading curing membrane meeting the requirements of ASTM C-309 Type 1 Class B. It is additionally formulated to act as a primer for many finishes or to seal concrete surfaces and provide a degree of abrasion to flatwork.

Specification clause **MasterKure 106** Where indicated, concrete shall be cured by application of MASTERKURE 106, membrane forming wax emulsion manufactured by BASF Middle East or similar approved; to the following specification:

## SPECIFICATION TYPE:

ASTM C309: Type 1 Class A AASHTO M-148

**MasterKure 106** is to be applied at a coverage rate of 5 to 6 square metres per litre and strictly in accordance with the manufacturer's instructions.

## QUALITY STATEMENT

This statement is made under condition that the material and usage thereof conform to the terms of our published literature and recognized good workmanship

BASF JO 03/2014

## Storage

Shelf life is up to 6 months when stored under cover, out of direct sunlight and protected from extremes of temperature.

## HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

## Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Basf representative.

Basf reserves the right to have the true cause of any difficulty determined by accepted test methods.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labor involved in the application are beyond our control

**As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.**