

MasterLife[®] WP707

(Formerly known as Rheomac 707)

Low dosage, liquid, integral waterproofer

DESCRIPTION

A liquid admixture for concrete to give high water resistance, based upon a blend of surface active agents and refined lignosulphonate. Waterproof concrete is the result of good concrete practice coupled with the lowest w/c ratio compatible with achieving full compaction. The use of **MasterLife WP707** enables all these criteria to be met due to its strong plasticising and water reducing properties.

PRIMARY USES

MasterLife WP707 should be used in all structural concrete that is constantly or intermittently in contact with water such as sea walls, tunnels, basements, structural and precast concrete in exposed superstructures.

ADVANTAGES

- Concrete containing **MasterLife WP707** is resistant to water penetration either under conditions of hydrostatic pressure or capillary absorption.
- Durability is increased due to a significant reduction in w/c ratio.
- Sulphate attack is reduced due to the sulphate bearing ground water being resisted.
- The cohesive properties of the concrete are improved thus reducing segregation and bleeding.
- Concrete of similar workability to a control mix produced with **MasterLife WP707**, is easier to place.
- Pumpability of concrete is greatly improved.
- The surface finish of the concrete is improved.

PACKAGING

MasterLife WP707 is available in bulk or 210 litre drums.

ACTION

water resistant concrete by its two fold action:
MasterLife WP707 assists in the production of
I. It significantly reduces water demand to enable production of good workability concrete with a minimum water/cement ratio.
II. It disrupts the cellular network within the

concrete mass (capillaries), that are normally interconnected thereby reducing the concrete permeability. Test results using Initial Surface Absorption Tests (ISAT) in accordance with BS 1881: Part 5: 1970, on concrete with **MasterLife WP707** show a decrease in surface absorption of between 60-80% over a similar concrete without **MasterLife WP707**

COMPOSITION

A blend of specially selected surface active agents and refined lignosulphonates.

TYPICAL PROPERTIES

Properties listed are only for guidance and are not a guarantee of performance

Colour:	Brown liquid. Specific gravity: 1.185 at 25°C.
Air entrainment:	2 ± 1% according to grading of sand and water content.
Chloride content:	Nil to BS 5075.
Nitrate content:	Nil.
Freezing point::	0°C. Can be reconstituted if stirred after thawing.

STANDARDS

ASTM C494: Types A & D.

DIRECTIONS FOR USE

MasterLife WP707 should be added with the mixing water preferably via a dispenser. It should never be added to the dry cement. No extension to mixing times are required.

POINTS TO REMEMBER WHEN PRODUCING WATERPROOF CONCRETE:

- Ensure specified water / cement ratio is not exceeded; work within the range of 0.4 to 0.6.
- Keep water content as low as possible
- compatible with achieving full compaction.
- Place concrete quickly and ensure it is thoroughly compacted.

MasterLife[®] WP707

(Formerly known as Rheomac 707)

- Protect new concrete against rapid drying out and ensure adequate and complete curing with BASF's **MASTERKURE** curing compounds.

DOSAGE

320ml per 100kg of cement. Field trials should be conducted to determine the effect of **MasterLife WP707** on the workability of the concrete.

EFFECTS OF OVER DOSAGE

- Slight set retardation. (No effect on striking times).
- Slight increase in air content.
- Increase in workability.

SPECIAL FEATURES

Advantage of **MasterLife WP707**'s strong plasticising action must be taken to reduce water contents to a minimum. A reduction in w/c ratio in the region of 10 to 15% can generally be achieved.

DISPENSING

MasterLife WP707 should be dispensed through a proprietary dispenser such as those available from BASF. Details upon request.

TYPICAL TEST RESULTS

Table 1 - Water absorbency

Mix Proportions:	Series I	Series II
Cement	340kg	400kg
Sand	650kg	585kg
20mm-5mm aggregate	1280	1285
Workability	50mm	100mm

	Series I		Series II	
	None	RHEOMAC 707 at 320ml / 100kg cement	None	RHEOMAC 707 at 320ml / 100kg cement
Cement	SRC	SRC	OPC	OPC
Air %	1	3	1	3
W/C	0.5	0.44	0.43	0.37
Density kg/m ³	2.43	2.43	2.45	2.43
Water absorbency after 2 hours	4.6	2.0	4.1	1.8

Table

Reference:	Initial surface absorption (ml/m ² /sec)			
Control	10 min	30 min	1 hour	2 hour
1	2.04	1.15	0.87	0.73
2	2.58	1.77	1.44	1.28
3	2.33	1.61	1.35	1.23
Average	2.31	1.51	1.22	1.08
RHEOMAC [®] 707				
1	0.98	0.48	0.34	0.24
2	1.09	0.56	0.41	0.28
3	0.60	0.35	0.27	0.20
Average	0.89	0.46	0.34	0.24



The Chemical Company

MasterLife[®] WP707

(Formerly known as Rheomac 707)

ANALYSIS OF RESULTS

The typical results above show that **MasterLife WP707** is effective as a permeability reducing admixture both under conditions of pressure and capillary absorption. It can be used with complete safety with OPC and SRC cements. That it significantly lowers water cement ratio whilst maintaining workability without affecting compressive strength.

All products should be used in accordance with the manufacturer's instructions. No responsibility can be taken by the manufacturer where conditions of use are beyond our control.

STORAGE

Store under cover, out of direct sunlight and protect from extremes of temperature.

SAFETY PRECAUTIONS

MasterLife WP707 contains no hazardous substances requiring labelling. For further information, refer to material safety data sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

This statement is made under condition that the material and usage thereof conform to the terms of our published literature and recognized good workmanship

BASF JO 03/2014

® = Registered trademark of the BASF-Group in many countries.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labor involved in the application are beyond our control

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals – Jordan

Tel: +962-6 5521672

<http://www.basf-cc.com.jo/>

P.O. Box 752 ,11118, Amman, Jordan

Fax: +962 6 5523148

e-mail: enquirycc.neareast@basf.com